



CLEAR SEAL

PRODUCT NAME

CLEAR SEAL

MANUFACTURER & DISTRIBUTOR
OF INDUSTRIAL CHEMICALS
1611 GUNN HIGHWAY
ODESSA, FLORIDA 33556
(813) 886-8811

PRODUCT DESCRIPTION

A solvent-based concrete sealer formulated with acrylic resins designed for deep penetration. **CLEAR SEAL** is resistant to salt-spray, acids, alkali, water, ultraviolet rays, and wet and dry abrasion. The resin system, which has been specially formulated by a custom manufacturer, has a very high resistance to traffic, and the aromatic and aliphatic solvents incorporated into our system provide excellent penetration, flow and cure characteristics. Highly recommended for exterior use.

ALTERNATE USES

- a. Stamped Concrete Coating
- b. Kool Deck or Keystone
- c. Tennis Courts (Concrete Only)
- d. Shuffleboard Courts
- e. Swimming Pool Coating (highly resistant to water, acids and pH variations).
- f. Properly-prepared Steel Surfaces.
- g. As a Water Proof, Sun Proof, and a Decorative Top Coating for Masonry Roofs and Walls.

LIMITATIONS

Do not use on wood surfaces. Do not use on areas sensitive to solvent attack. Do not use on wet surfaces.

MAINTENANCE

CLEAR SEAL has high resistance to water, alkali, and abrasion. Clean, as needed, with soap/detergent and water. Rinse after cleaning. If the surface begins to dull due to extensive use (typically 3-4 years) an additional coat of CLEAR SEAL will restore the original luster of the floor.

APPLICATION

Preparation: Concrete must be at least 10 days old. All old paint, oil, and grease must be removed. It is required that most concrete must be etched as a porous surface. Etching should be done with 5 parts water to 1 part Muriatic Acid Solution. Extremely hard or polished concrete may require a second application with a stronger solution. Rinse surface thoroughly with plenty of clean water and let dry completely.

Roller Application: Do not pour **CLEAR SEAL** directly on surface. Apply **CLEAR SEAL** at a rate not to exceed 250 ft² per gallon. Use a roller pan or grid to remove excess sealer. A second coat should be applied after the first coat has completely dried, usually after a minimum of 1-2 hours. Additional coats will increase the surface gloss.

Spray Application: Use an airless sprayer with a medium tip size and very low pressure. If conditions are windy or extremely hot, adjust technique to avoid "dry spraying" the surface. A second coat should be sprayed after the first coat is dry.

Cleanup: Use toluene, xylene, or **INCRETE STAIN REDUCER** for cleaning tools.

TECHNICAL DATA

Specific Gravity:	0.905
Non-volatile (wt):	19-20%
Wetherometer G23F Type:	2000+hrs.
Moisture Vapor Permeability:	0.001
Hurricane Force Water:	No Effect
Abrasion Resistance:	12.5 g. loss
Toukon Hardness:	12 (KHN)
Glass Transition Temperature:	50°C
Flash Point:	65°F
Coverage:	250ft ² /gal
Min. Working Temperature	50°F

ACID&ALKALI RESISTANCE TEST

Each sample was allowed to react for 24 hours under a watch glass, washed with water, allowed to recover for 30 minutes then observed:

Alkali	
2% NaOH	Slight Dulling
5% Tide	No Effect
2% Ivory	No Effect

ACID	
5% Citric Acid	No Effect
Milk (Lactic Acid)	No Effect
5% HCl	No Effect
5% Phosphoric Acid	No Effect
Mustard	Slight Stain
Ketchup	No Effect

SAFETY PRECAUTIONS

FLAMMABLE: Keep away from heat, sparks, and open flame. Ventilate area, do not let vapors accumulate. Material can be irritating to eyes and skin. In case of contact, flood affected area with water. See a Physician if irritation persists. Avoid prolonged breathing of vapors. Use approved organic vapor mask when TLV is exceeded. **KEEP AWAY FROM CHILDREN.**

PACKAGING

1 gallon, 5 gallon pail, 55 gallon drum

AVAILABILITY AND COST

Available through a large network of paint dealers located throughout the USA. For availability in other areas, contact manufacturer. Cost will vary with location.

TECHNICAL SERVICES

Over 40 years of sealer manufacturing makes **INCRETE** personnel the most knowledgeable in the field of concrete sealers. A highly educated and well-trained technical staff is available. Call or contact (813) 886-8811.

WARRANTY

All recommendations, statements and technical data contained herein based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his use of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person having any injury, loss or damage directly or indirectly resulting from use of or inability to use the product.

Recommendations or statements other than those contained in written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

IMPORTANT NOTICE

THESE PRODUCTS ARE SOLD SUBJECT ONLY TO THE EXPRESSED WARRANTIES CONTAINED HEREIN. ADDITIONAL WARRANTIES, EXPRESSED OR IMPLIED, AND ANY WARRANTY OF MERCHANT ABILITY IS HEREBY EXCLUDED. BUYER AGREES THAT SELLER ASSUMES NO LIABILITY FOR CONSEQUENTIAL DAMAGES OF ANY KIND, WHICH RESULT FROM THE USE OR MISUSE OF THE MERCHANDISE SOLD HEREUNDER. IN THE EVENT THAT THE BUYER PROVES THAT ANY GOODS RECEIVED DO NOT CONFORM TO THE SPECIFICATIONS AGREED TO BETWEEN THE PARTIES OR IF THE BUYER PROVES THAT SUCH GOODS WERE DEFECTIVELY MANUFACTURED. THE BUYER'S REMEDIES SHALL BE LIMITED TO EITHER THE RETURN OF THE GOODS AND REPAYMENT OF THE PURCHASE PRICE OR REPLACEMENT OF THE NON-CONFORMING GOODS AT THE OPTION OF THE SELLER. SUCH REMEDY BEING EXCLUSIVE OF ALL OTHERS AND THE SOLE REMEDY AVAILABLE TO THE BUYER, HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES.